

(19)

Generated Document.

PATENT ABSTRACTS OF JAPAN(21) Application number: **09040065**(51) Intl. Cl.: **C08L 23/00 C08L 67/00**(22) Application date: **07.02.97**

(30) Priority:	(71) Applicant: KURARAY CO LTD
(43) Date of application publication: 18.08.98	(72) Inventor: YAMASHITA TAKASHI KUKI TORU MASUDA HARUHISA TAKAMOTO KATSUNORI NAKADA HIROMICHI
(84) Designated contracting states:	(74) Representative:

BEST AVAILABLE COPY

(54) MODIFIER FOR POLYMER

(57) Abstract:

PROBLEM TO BE SOLVED: To obtain a modifier for common use for various polymer types, capable of improving their physical properties, e.g. resistance to shock, without causing, e.g. loss of fluidity or gelation.

SOLUTION: This modifier for polymers comprises a polyester-based copolymer and olefin-based polymer, wherein the former has an addition polymer block composed of a polyester block and the following addition polymer block II-1 and/or II-2. Addition polymer block II-1: comprises a polymer block (A) composed of an aromatic vinyl compound polymer block and/or polybutadiene block with the partially (below 30mol%) hydrogenated 1,2-bond, and a polymer block (B) composed of hydrogenated polyisoprene block, polybutadiene block with the partially (30 to 80mol%) hydrogenated 1,2 bond and/or hydrogenated isoprene/butadiene copolymer block. Addition polymer block II-2: comprises an aromatic vinyl compound polymer block (C) and isobutylene polymer block (D).

COPYRIGHT: (C)1998,JPO

BEST AVAILABLE COPY